polytec

Last updated **October, 2026**

Technical Data

Light Reflectance Value (LRV)

Light Reflectance Value (LRV)

Light reflectance value (LRV), is a measure of visible and usable light that is reflected from a surface when illuminated by a light source. The table below shows the average LRV values measured for a range of **polytec** Melamine doors & panels colours.

The colour tone of wood grain prints and stone structures can differ significantly depending on the position of the surface area measured. Generally it is difficult to get a consistent LRV value for wood grain or stone patterns and the value shown is an average unlike solid colours which reflect a consistent result.

Colour	LRV
Adriatic	8.6
Alabaster	83
Alboran Stone	66
Alicante Stone	65.6
Amaro	63.7
Argento Stone	69.5
Athena Stone	8.3
Avion Grey	57.8
Barrington Marble	10.2
Batten Oak	26.9
Beige Travertine	55.2
Bernini Marble	32.3
Bespoke	41.4
Black	6
Black Wenge	7.4
Blackened Oak	7.9
Blanco Marquina	73.5
Bleached Walnut	65.7
Blonde Oak	50.2
Blossom White	81.4
Bone White	83.1
Boston Oak	33.6
Botany Oak	33.7
Bottega Oak	8.6
Bronzed Oak	11.8
Buller Stone	77.6
Café Oak	12.3
Calacatta D'Oro	71.2
Calacatta Grey	65.1
Canterbury Grey	17.9
Carrara	70.9
Castel	32.7
Catalina Marble	7.6
Chambord	74.9
Cinder	10.1
Classic White	86.7
Cosmic Granite	12.6
Crisp White	86.1

Colour	LRV
Dark Batten Oak	8.8
Dawnshade	63.56
District Oak	11
Drifted Oak	52.7
Ecru Oak	41.5
Empire Oak	10.4
European Walnut	14.3
Ferro	11.5
Florentine Walnut	15.8
Fontaine	44.2
Forage	14.6
Grey Cement	38.3
Grey Taj	45
Greystone	24.9
Habitat	12.6
Hazel Oak	17.5
Ivorio Travertine	63.1
Jamaican Walnut	8
Laurel Oak	44.7
Maison Oak	31.4
Malt	52.9
Manor Oak	28.6
Marmo di Monte	64.6
Marmo di Torre	70.7
Natural Oak	40.3
New Ultra White	92
Notaio Walnut	17.8
Oxford	6
Oyster Grey	56
Pallido	51.3
Papyrus	75.2
Polar White	88.1
Portland Stone	39.2
Portofino Stone	57.4
Prime Oak	28.4
Roman Ceppo	34.3
Rubra Oak	10.9
Shannon Oak	8.3

Colour	LRV
Silk	62.9
Snow Fabrini	74.9
Society Oak	17.8
Soft Walnut	55.7
Stone Grey	36.5
Taj Mahal	57
Tasmanian Oak	30.4
Taupe	31
Titanium	15.3
Tivoli Ceppo	62.9
Topiary	22.3
Tuross Oak	41.3
Ultra White	92
Verdelho	52
Veusvius Ceppo	19
White Cement	59.2
White Cotton	82.9
Whitewood	68.8
Wispwood	49.05

Contact

For further information contact:

Porta Products Pty. Ltd. (NZBN 9429052693182)

Address 9 Beale Place, East Tamaki
Auckland 2013,
New Zealand

Telephone 0800 220 607

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.