

polytec

Technical Data Sheet

**LRV**

Light Reflectance Value

## LRV Light Reflectance Value / Technical Data Sheet

### LRV LIGHT REFLECTANCE VALUE

Light reflectance value (LRV), is a measure of visible and usable light that is reflected from a surface when illuminated by a light source. The table below shows the average LRV values measured for a range of polytec Melamine doors & panels colours.

The colour tone of wood grain prints and stone structures can differ significantly depending on the position of the surface area measured. Generally it is difficult to get a consistent LRV value for wood grain or stone patterns and the value shown is an average unlike solid colours which reflect a consistent result.

COLOUR	FINISH	LRV
Adriatic	Smooth	8.6
Avion Grey	Venette	57.8
Black	Matt	5.4
Black	Venette	4.6
Black	Woodmatt	6
Black Wenge	Ravine	7.4
Blackened Oak	Woodmatt	7.9
Blonde Oak	Woodmatt	50.2
Boston Oak	Woodmatt	33.6
Botany Oak	Woodmatt	33.7
Bronzed Oak	Woodmatt	11.8
Café oak	Ravine	12.3
Canterbury Grey	Matt	17.9
Classic White	Matt	86.7
Classic White	Sheen	84.9
District Oak	Woodmatt	11
Drifted Oak	Ravine	52.7
Ecru Oak	Woodmatt	41.5
Forage	Smooth	14.6
Grey Cement	Smooth	38.3
Habitat	Smooth	12.6
Hazel Oak	Woodmatt	17.5
Laurel Oak	Woodmatt	44.7
Maison Oak	Ravine	31.4
Manor Oak	Woodmatt	28.6
Natural Oak	Ravine	40.3
Oyster Grey	Matt	56
Polar White	Matt	88.1
Rubra Oak	Woodmatt	10.9
Shannon Oak	Matt	8.3
Society Oak	Woodmatt	17.8

COLOUR	FINISH	LRV
Soft Walnut	Ravine	55.7
Stone Grey	Matt	36.5
Taupe	Matt	31
Titanium	Matt	15.3
Topiary	Smooth	22.3
Tuross Oak	Matt	41.3
New Ultra White	Venette	92
White Cement	Smooth	59.2
Whitewood	Matt	68.8

### CONTACT

For further information contact:

**Porta Limited** (NZBN 9429052693182)

**Address** 9 Beale Place, East Tamaki  
Auckland 2013,  
New Zealand

**Telephone** 0800 220 607

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.